

## Scapa 3160

### Waterproof Cloth Tape - standard grade

---

#### DESCRIPTION

Scapa 3160 is a standard grade, polyethylene laminated, waterproof cloth tape, coated with a pressure sensitive natural rubber resin adhesive. Scapa 3160 is available in black, white and silver.

#### APPLICATIONS

- Designed as an all purpose duct tape for general purpose applications.
- Used for sealing, bundling, short term masking and protecting.
- Excellent for jointing polyethylene sheeting in asbestos removal applications.
- Double glazing unit sealing.
- Medium temperature duct sealing within HVAC.
- Carpet joining and edging.

#### PRODUCT BENEFITS

- Good water resistance.
- Excellent adhesion and strength.
- Flexible and conformable.
- Easy tear.
- Good low temperature performance.
- Good all purpose product.
- Service temperature: -15°C to +75°C.

## TECHNICAL PROPERTIES

| Technical Property  | Nominal Value | Unit | Test Method |
|---------------------|---------------|------|-------------|
| Adhesion to Backing | 3.0           | N/cm | IEC 60454-2 |
| Adhesion to Steel   | 5.0           | N/cm | IEC 60454-2 |
| Breaking Strength   | 35            | N/cm | IEC 60454-2 |
| Thickness           | 0.15          | mm   | AFERA 5006* |

*Note:*

*\*\*\*This will be taken from the core product for the SAP Material Group\*\*\**

## STANDARD PRESENTATIONS

- Core: Cardboard
- Packaging: Bulk packed using interleaving sheets between layers./Shrink wrapped in packs of 4 \*
- Roll Length: 25m, 50m
- Roll Width: 19mm, 25mm, 38mm, 50mm, 75mm, 100mm

*Note:*

*Note: Information on stock items, non-standard sizes and colours, and lead times is available on request*

*\*Dependant on size/colour combination*

## RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging, until required for use. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Shelf life will vary with conditions of use and is affected by climatic environment, but under these conditions, it is recommended that this product should be used within two years from date of manufacture.