

BARNIER® 9080S

80°C Paper masking Adhesive Tape

DESCRIPTION

Barnier 9080S is a semi creped paper with a total thickness of 125µm coated with a solvent rubber adhesive. Smooth paper 80 ° C. Masking paint in industry and car body.

APPLICATIONS

- Automotive aftermarket masking tape with short term oven baking resistance.
- Premium masking tape in industry as well as for house painters for indoor use 5 days
- Suitable for all general purpose 80°C indoor bonding, holding, sealing and masking applications.

PRODUCT BENEFITS

- Clean and easy removal.
- Flexible and easy to use
- No staining
- Resistant to chemicals, lacquers and solvents
- Good shear and holding strength.
- Continuous temperature resistance: +80°C.
- Resistant to oven baking.
- Excellent paint flake resistance.

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
Adhesion to Steel	2.3	N/cm	AFERA 5001
Elongation at Break	10	%	AFERA 5004
Tensile Strength	32	N/cm	AFERA 5004
Total Thickness	125	µm	AFERA 5006

Note:

****This will be taken from the core product for the SAP Material Group****

STANDARD PRESENTATIONS

- Colours: Natural
- Dimension : 50mx19mm; 50mx25mm; 50mx38mm; 50mx50mm
- Branding: Barnier
- Core: 76mm Scapa or Barnier branded cardboard core
- Packaging: 48; 36; 24; 24

RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C. Under these conditions, the storage life of the tape in a temperate climate should not exceed 12 months.

Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.

Scapa masking tapes are not suitable for outdoor exposure and should not be submitted to prolonged periods of sunlight, as tapes may become difficult to remove. Clean removal may also vary with surface type, lacquers, primers and paints nature as well as the temperature of the surface at removal. For best results, remove the tape as soon as possible after applying the paints pulling it slowly at a 90° angle with constant speed